



MEATLONN™
Fibrous Casing

www.futamuragroup.com

MEATLONN™

Fibrous Casing

Excellent Strength & Extraordinary Uniformity of Stuffed Diameter

MEATLONN™ Fibrous casings are manufactured by forming a special thin paper made from selected abaca fiber into a continuous tube which is then impregnated with viscose prepared from wood pulp.

Features

- Excellent Strength
- Reliable Size Consistency
- Moderate Permeability to moisture and smoke
- Great Machineability at High Speed Stuffing
- Flexible Convertibility
- Easy Disposing

INTERIOR TREATMENT

MEATLONN™ V TYPE

MEATLONN™ V Type "Regular"

Best for cooked and smoked sausages such as bologna, mortadella, cooked salami, dry sausages.

MEATLONN™ V type is a regular type of fibrous casing for cooked and smoked sausages which do not require special peeling or adhesion feature of casings for the encased products throughout the process.



MEATLONN™ E TYPE



MEATLONN™ E type "Easy Peel"

Best for cooked and smoked ham, and the products to be sliced in the factory as well as processed and smoked cheese.

MEATLONN™ E type is an easy peelable type of fibrous casing. The inner surface of this fibrous casing is specially treated during its production so that it is easy peelable from the encased product without disrupting the product's surface.

MEATLONN™ G TYPE

MEATLONN™ G type "Good Adhesion"

Best for Dry and Semi-dry sausages such as salami, pepperoni, summer sausage and more.

MEATLONN™ G type is a good adhesion type of fibrous casing. The inner surface of this fibrous casing is specially treated during its production so that it may adhere to and shrink with the encased products as it dries.



CONVERSIONS

MEATLONN™ fibrous casing may be supplied in the form of cut pieces in requested length, in bundles as well as on reel. Additionally, the following conversions are available for customizing to your production:

1. PRE-STICKING

Pre-sticking casing reduces the possibility of jelly, fat or air pocket formation on the finished products. Optimal size of pre-sticking holes and patterns can be selected among the wide variety.

2. VENT HOLES

In order to use cut, tied or clipped casing efficiently on some type of product, it is necessary to drill vent holes adjacent to the tied or clipped end of casing for quick release of air during stuffing.

3. PRINTING

Casing can be printed. Please contact us for the details of available printing.

4. SHIRRING

Mechanically shirred casing ensures great increase of productivity at stuffing process.

5. RTU Casing

RTU casing is pre-moistened in order to allow for immediate use.

COLORS

The wide variety of colors are available such as mahogany, red, white, amber as well as clear.

USAGE

MEATLONN™ fibrous casing should be soaked in lukewarm water 30° - 40°C (86° - 104°F) at least for 30 minutes before use in order to obtain the optimal features of casing.

MEATLONN™ fibrous casing can be stuffed out up to our recommended maximum stuffed diameter (RMSD) without break. Beyond the RMSD, breakage of casing may occur.

For sanitary purpose and retention of quality of casing, once soaked, casing should be consumed within the same day. Unused and not soaked fibrous casings should be put in a polyethylene and/or similar kind of bag when stored for a few days. Casing should be protected against abrasion and not be contacted with hard and rough surface directly.

STORAGE

MEATLONN™ fibrous casing should be kept in original packaging at 15°-25°C (59° - 77° F) and relative humidity of 60-70% before using. Avoid direct sunlight.



SIZE CHART

| Casing Size | | Recommended Stuffing Diameter | |
|-------------|--------|-------------------------------|------|
| Caliber | Code | mm | inch |
| 36 | 2/5T | 37.5 | 1.48 |
| 38 | 3/5 | 40 | 1.57 |
| 41 | 41T | 41 | 1.61 |
| 43 | 4/5 | 43.5 | 1.71 |
| 44 | 1SS | 45 | 1.77 |
| 45 | 1S | 47.5 | 1.87 |
| 46 | 1SL | 49 | 1.93 |
| 48 | 1 | 50.5 | 1.99 |
| 49 | 1F | 51 | 2.01 |
| 49 | 1FM | 51.5 | 2.03 |
| 51 | 1-1/8 | 53.5 | 2.11 |
| 52 | 1-1/4 | 55 | 2.17 |
| 55 | 1-1/2 | 56.5 | 2.22 |
| 56 | 2ST | 58.5 | 2.30 |
| 58 | 2 | 61.5 | 2.42 |
| 60 | 2-1/4 | 66.5 | 2.62 |
| 60 | 2-1/4L | 67.5 | 2.66 |
| 65 | 2-1/2S | 70.5 | 2.78 |
| 68 | 2-1/2 | 71.5 | 2.81 |
| 69 | 3-1/2S | 74.5 | 2.93 |
| 70 | 3-1/2L | 76.5 | 3.01 |
| 71 | 4SS | 78 | 3.07 |
| 73 | 4S | 80 | 3.15 |
| 75 | 4 | 82 | 3.23 |
| 78 | 4L | 84 | 3.31 |
| 80 | 5 | 88 | 3.46 |

| Casing Size | | Recommended Stuffing Diameter | |
|-------------|--------|-------------------------------|------|
| Caliber | Code | mm | inch |
| 83 | 5L | 90 | 3.54 |
| 85 | 5-1/2 | 92.5 | 3.64 |
| 87 | 5F | 94 | 3.70 |
| 88 | 5M | 96.5 | 3.80 |
| 90 | 5N | 97.5 | 3.84 |
| 93 | 6MS | 101 | 3.98 |
| 95 | 6M | 103.5 | 4.07 |
| 102 | 6SL | 105.5 | 4.15 |
| 105 | 6-1/2 | 107.5 | 4.23 |
| 107 | 6-1/2L | 109 | 4.29 |
| 108 | 7S | 111 | 4.37 |
| 110 | 7 | 114 | 4.49 |
| 112 | 7L | 117 | 4.61 |
| 115 | 7-1/2 | 119 | 4.69 |
| 120 | 8 | 123.5 | 4.86 |
| 125 | 8-1/2 | 128 | 5.04 |
| 130 | 9 | 132 | 5.20 |
| 132 | 9L | 134 | 5.28 |
| 135 | 9-1/2 | 139 | 5.47 |
| 137 | 9-1/2L | 143 | 5.63 |
| 140 | 10 | * | * |
| 150 | 11 | * | * |
| 155 | 11L | * | * |
| 165 | 12 | * | * |
| 195 | 14S | * | * |
| 200 | 14 | * | * |

*Please contact us for the details.

Sales Offices

Americas

Futamura USA, Inc.
369 Lexington Avenue, 2nd Floor,
New York, NY, 10017 USA
Toll Free: +1-800-965-5144
Tel: +1-646-556-6652
Email: casing@futamura.com

Asia-Pacific

Futamura Chemical Co., Ltd.
2-29-16 Meieki, Nakamura-ku,
Nagoya, Aichi, 450-0002, Japan
Email: info@futamura.co.jp

Europe

Futamura Chemical UK Ltd.
Station Road, Wigton,
Cumbria CA7 9BG, United Kingdom
Email: info@futamura.com

For more information, please visit www.futamura.com

Disclaimer: Futamura Chemical Company, or any of its affiliated companies (hereinafter 'Futamura') declines any liability with respect to the use made by any third party of the information contained herein. The information contained herein represents Futamura's best knowledge thereon without constituting any express or implied guarantee or warranty of any kind (including, but not limited to, the accuracy, the completeness or relevance of the data set out herein). Futamura is the sole owner or authorised user of the intellectual property rights relating to the information communicated. The information relating to the use of the products is given for information purposes only. No guarantee or warranty is provided that the product is adapted to the client's specific use. The client should perform his own tests to determine the suitability for a particular purpose. The final choice of use of a product remains the sole responsibility of the client.